



XYPEX AUSTRALIA
C-1000NF 3KG SOLUBLE BAG
DOSAGE CHART



Kg	M3	M3	M3	M3	M3	M3	M3	M3	M3	M3	M3	M3	M3	M3	M3	M3	M3	M3	M3	M3	M3
Cementitious	3.0	3.2	3.4	3.6	3.8	4.0	4.2	4.4	4.6	4.8	5.0	5.2	5.4	5.6	5.8	6.0	6.2	6.4	6.6	6.8	7.0

250	2			3	3	3	3	3		4	4	4	4	4	4	4	5	5	5	5	5
260				3	3	3	3			4	4	4	4	4	5	5	5	5	5	5	5
270			3	3	3	3			4	4	4	4	4	5	5	5	5	5	5	5	6
280			3	3	3	3		4	4	4	4	4	5	5	5	5	5	5	5	6	6
290		3	3	3	3		4	4	4	4	4	5	5	5	5	5	5	5	6	6	6
300	3	3	3	3		4	4	4	4	4	5	5	5	5	5	5	5	6	6	6	6
310	3	3	3	3		4	4	4	4	4	5	5	5	5	5	5	6	6	6	6	6
320	3	3	3		4	4	4	4	4	5	5	5	5	5	5	6	6	6	6	6	7
330	3	3	3		4	4	4	4	5	5	5	5	5	5	6	6	6	6	6	7	7
340	3	3		4	4	4	4	4	5	5	5	5	5	6	6	6	6	6	7	7	7
350	3	3		4	4	4	4	5	5	5	5	5	6	6	6	6	6	7	7	7	7
360	3		4	4	4	4	5	5	5	5	5	6	6	6	6	6	6	7	7	7	7
370	3		4	4	4	4	5	5	5	5	5	6	6	6	6	6	7	7	7	7	7
380		4	4	4	4	5	5	5	5	5	6	6	6	6	6	7	7	7	7	7	8
390		4	4	4	4	5	5	5	5	5	6	6	6	6	7	7	7	7	7	8	8
400	4	4	4	4	5	5	5	5	5	6	6	6	6	7	7	7	7	7	8	8	8
410	4	4	4	4	5	5	5	5	5	6	6	6	6	7	7	7	7	8	8	8	8
420	4	4	4	5	5	5	5	5	6	6	6	6	7	7	7	7	7	8	8	8	8
430	4	4	4	5	5	5	5	6	6	6	6	6	7	7	7	7	8	8	8	8	9
440	4	4	4	5	5	5	5	6	6	6	6	7	7	7	7	8	8	8	8	9	9
450	4	4	5	5	5	5	6	6	6	6	7	7	7	7	8	8	8	8	8	9	9
460	4	4	5	5	5	5	6	6	6	6	7	7	7	7	8	8	8	8	9	9	9
470	4	4	5	5	5	6	6	6	6	7	7	7	7	8	8	8	8	9	9	9	9
480	4	5	5	5	5	6	6	6	6	7	7	7	7	8	8	8	8	9	9	9	10
500	4	5	5	5	6	6	6	6	7	7	7	7	8	8	8	8	9	9	9	10	10

NB SOLUBLE BAGS NOT RECOMMENDED IN THESE INSTANCES.

 PRODUCT SHOULD BE WEIGHED FOR DOSING.

NB: Cementitious includes GGBFS, Fly Ash, GP, SF.

NB: XYPEX Admix C1000NF must always be dosed at a rate not less than 0.80% of cementitious and

not more than 1.0% of cementitious unless otherwise recommended by XYPEX Australia Specifications.

NB: For any mixes where cementitious content is other than shown above please contact your nearest XYPEX

Distributor Telephone 02 6040 2444

NB: PRODUCT MUST BE ADDED TO THE AGITATOR PRIOR TO THE ADDITION OF WATER/AGGREGATES/OR CEMENT.