



XYPEX AUSTRALIA
C5000 2.5KG SOLUBLE BAG
DOSAGE CHART



Kg	M3	M3	M3	M3	M3	M3
Cementitious	1	3.0	5.0	5.4	6.0	7.0

350			4	4	5	5
360			4	4	5	6
370			4	4	5	6
380			4	5	5	6
390			4	5	5	6
400			4	5	5	6
410	1	3	5	5	5	6
420	1	3	5	5	6	6
430	1	3	5	5	6	7
440	1	3	5	5	6	7
450	1	3	5	5	6	7
460	1	3	5	5	6	7
470	1	3	5	6	6	7
480	1	3	5	6	6	7
490	1	3	5	6	6	7
500	1	3	5	6	6	7

NB SOLUBLE BAGS NOT RECOMMENDED IN THESE INSTANCES.

PRODUCT SHOULD BE WEIGHED FOR DOSING.

NB: Cementitious includes GGBFS, Fly Ash, GP, SF.

NB: XYPEX Admix C5000 must always be dosed at a rate not less than 0.50% of cementitious and not more than 0.6% of cementitious unless otherwise recommended by XYPEX Australia Specifications.

NB: For any mix where cementitious content is other than shown above please contact XYPEX Australia, Telephone 02 60402444

NB: PRODUCT MUST BE ADDED TO THE AGITATOR PRIOR TO THE ADDITION OF WATER/AGGREGATES/OR CEMENT.