

PO Box 1751
Adelaide SA 5001

250 Victoria Square
Adelaide SA 5000

Tel: 1300 653 366
Fax: 1300 883 171



Internet: www.awqc.com.au

Email: producttesting@awqc.com.au

Xypex Australia
Attn: Joshua Hall
76 Merkel Street
Thurgoona
NSW 2640
AUSTRALIA

12/11/2020

Dear Joshua,

Please find the attached report to AS/NZS 4020:2018 for Xypex Admix C-5000 Concrete Additive submitted for testing.

Should you have any enquiries about the report or any other matters pertaining to the Standard please contact the laboratory on 61 8 7424 1512

Yours sincerely,

Michael Glasson
Supervisor Product Testing



Corporate Accreditation No.1115
Chemical and Biological Testing
Accredited for compliance with ISO/IEC 17025





Internet: www.awqc.com.au

Email: producttesting@awqc.com.au

FINAL REPORT

Report ID : 295678

Report Information

Submitting Organisation : 00109093 : Xypex Australia
Account : 130086 : Xypex Australia
AWQC Reference : 130086-2019-CSR-15 : Prod Test: Xypex Admix C-5000 Concrete Additive (App H & Clause
Project Reference : PT-4385
Product Designation : Xypex Admix C-5000 Concrete Additive
Composition of Product : Concrete Additive (see Product Data Sheet and MSDS from PT-3934).
Product Manufacturer : Xypex Australia, Thurgoona, NSW, AUSTRALIA.
Use of Product : In-Line/Concrete Additive.
Sample Selection: As provided by the submitting organisation
Testing Requested : **AS/NZS 4020 TESTING OF PRODUCTS FOR USE IN CONTACT WITH DRINKING WATER**
Product Type : Composite
Samples : Samples were prepared and controlled as described in Appendix A of AS/NZS 4020:2018
Extracts : Extracts were prepared as described in Appendix/Clause H, 6.8.
Project Completion Date : 12-Nov-2020
Project Comment : The results presented herein demonstrate compliance of Xypex Admix C-5000 Concrete Additive to AS/NZS 4020:2018 when exposed at area to volume ratios up to 15000 mm²/L at 70°C ± 2°C. Refer to Test Report No. 259808 (Project Reference PT-3935).

PLEASE NOTE THAT THIS REPORT SHALL NOT BE REPRODUCED EXCEPT IN FULL

THE RESULTS STATED IN THIS REPORT RELATE TO THE SAMPLE OF THE PRODUCT SUBMITTED FOR TESTING. ANY CHANGES IN THE MATERIAL FORMULATION, PROCESS OF MANUFACTURE, THE METHOD OF APPLICATION, OR THE SURFACE AREA-TO-VOLUME RATIO IN THE END USE, COULD AFFECT THE SUITABILITY OF THE PRODUCT FOR USE IN CONTACT WITH DRINKING WATER

Michael Glasson
APPROVED SIGNATORY



Corporate Accreditation No.1115
Chemical and Biological Testing
Accredited for compliance with ISO/IEC 17025





Internet: www.awqc.com.au

Email: producttesting@awqc.com.au

FINAL REPORT

Report ID : 295678

Summary of Results

APPENDIX/CLAUSE	RESULTS
H – Metals	Passed at an exposure of 15000 mm ² per Litre.
6.8 – Organic Compounds	Passed at an exposure of 15000 mm ² per Litre.

Test Methods

Test(s) in Appendix	AWQC Test Method	Reference Method
H	TIC-006	EPA 200.8

Organic Test Methods

Test(s) in Clause	Test Method	Reference Method
Clause 6.8	TMZ-M36	USEPA524.2
	EP239	USEPA521
	EP132-LL	USEPA_SW846-8270D
	EP075C	USEPA_SW846-8270D
	EP075ASIM	USEPA_SW846-8270D

Summary Comment :

Three sequential soakings were performed to obtain a pH < 9.0. In accordance with section A8 (Cementitious Products). The sample was prepared and moist cured by the submitting organisation.



Corporate Accreditation No.1115
Chemical and Biological Testing
Accredited for compliance with ISO/IEC 17025



FINAL REPORT

Report ID : 295678

CLAUSE 6.7

Metals

Sample Description

The sample consisted of a cementitious cube measuring 25 mm x 25 mm x 25 mm providing an approximate surface area of 15000 mm² per Litre. Extracts were prepared using 1000 mL volumes of pre-conditioning water(AI 12.6).

Extraction Temperature

70°C ± 2°C.

Test Method

Metals (Appendix H)

Scaling Factor

Not applied.

Method of Analysis

All methods used to determine concentrations of metals are based on those described in the US EPA method 200.8 Determination of Trace elements in Waters and Wastes by Inductively Coupled Plasma - Mass Spectrometry. The methods have been adapted for the instrumentation in use at the Australian Water Quality Centre.

Concentration of the metals described in Table 2 of the AS/NZS 4020:2018 are determined as follows:

Aluminium, Antimony, Arsenic, Barium, Boron, Cadmium, Chromium, Copper, Iron, Lead, Manganese, Mercury, Molybdenum, Nickel, Selenium and Silver by Inductively Coupled Plasma Mass Spectrometry.

Results	Limit of Reporting mg/L	Blank mg/L	Test 1 mg/L	Test 2 mg/L	Max Allowed mg/L
Final Extract					
Aluminium	0.001	0.023	0.027	0.026	0.2
Antimony	0.0005	<0.0005	<0.0005	<0.0005	0.003
Arsenic	0.0003	<0.0003	<0.0003	<0.0003	0.01
Barium	0.0005	0.0290	0.0298	0.0310	0.7
Boron	0.020	<0.020	0.028	0.026	1.4
Cadmium	0.0001	<0.0001	<0.0001	<0.0001	0.002
Chromium	0.0001	0.0001	0.0004	0.0004	0.05
Copper	0.0001	0.1691	0.1504	0.1547	2.0
Iron	0.0005	0.0035	0.0100	0.0091	0.3
Lead	0.0001	0.0006	0.0008	0.0008	0.01
Manganese	0.0001	0.0008	0.0009	0.0006	0.1
Mercury	0.00003	<0.00003	<0.00003	<0.00003	0.001
Molybdenum	0.0001	0.0002	0.0003	0.0003	0.05
Nickel	0.0001	0.0059	0.0037	0.0039	0.02
Selenium	0.0001	<0.0001	<0.0001	<0.0001	0.01
Silver	0.00003	<0.00003	<0.00003	<0.00003	0.1

Evaluation

The product passed the requirements of clause 6.7 when tested at an exposure of 15000 mm² per Litre.

Number of Samples

1.

Test Comment

Not applicable.



Dzung Bui

APPROVED SIGNATORY



Corporate Accreditation No.1115
Chemical and Biological Testing
Accredited for compliance with ISO/IEC 17025





Internet: www.awqc.com.au

Email: producttesting@awqc.com.au

FINAL REPORT

Report ID : 295678

CLAUSE 6.8 Organic Compounds

Sample Description The sample consisted of a cementitious cube measuring 25 mm x 25 mm x 25 mm providing an approximate surface area of 15000 mm² per Litre. Extracts were prepared using 1000 mL volumes of pre-conditioning water(AI 12.6).

Extraction Temperature 70°C ± 2°C.

Test Method Organic Compounds (Clause 6.8). Max Allowed values are taken from the Australian Drinking Water Guidelines and Drinking-water Standards for New Zealand. Please note, some reported compounds have no guideline value.

Scaling Factor Not applied.

Results

Organic Compound

Nitrosamines	Blank µg/L	Test µg/L	Max Allowed
!External Lab Report No.	ES2035008	ES2035008	
1-Nitrosopiperidine (NPip)	<0.003	<0.003	
1-Nitrosopyrrolidine (NPyr)	<0.01	<0.01	
Nitrosomorpholine (NMor)	<0.003	<0.003	
N-Nitrosodiethylamine (NDEA)	<0.01	<0.01	
N-Nitrosodimethylamine (NDMA)	0.005	<0.003	0.1 µg/L
N-Nitrosodi-n-propylamine (NDPA)	<0.003	<0.003	
N-Nitrosomethylethylamine (NMEA)	<0.003	<0.003	

Organic Compound

Phenols	Blank µg/L	Test µg/L	Max Allowed
!External Lab Report No.	ES2035008	ES2035008	
2 4 5-trichlorophenol	<1.0	<1.0	
2 4 6-trichlorophenol	<1.0	<1.0	20 µg/L
2 4-dichlorophenol	<1.0	<1.0	200 µg/L
2 4-dimethylphenol	<1.0	<1.0	
2 6-dichlorophenol	<1.0	<1.0	
2-chlorophenol	<1.0	<1.0	300 µg/L
2-nitrophenol	<1.0	<1.0	
4-chloro-3-methylphenol	<1.0	<1.0	
m+p cresol	<2.0	<2.0	
o-cresol	<1.0	<1.0	
pentachlorophenol	<2.0	<2.0	9 µg/L
phenol	<1.0	<1.0	



Corporate Accreditation No.1115
Chemical and Biological Testing
Accredited for compliance with ISO/IEC 17025





Internet: www.awqc.com.au

Email: producttesting@awqc.com.au

FINAL REPORT

Report ID : 295678

Organic Compound

Phthalate Esters	Blank µg/L	Test µg/L	Max Allowed
!External Lab Report No.	ES2035008	ES2035008	
Bis(2-ethylhexyl) phthalate	<10	<10	10 µg/L
Butyl benzyl phthalate	<2	<2	
Di(2-ethylhexyl) adipate	<2	<2	
Diethyl phthalate	<2	<2	
Dimethyl phthalate	<2	<2	
Di-n-butyl phthalate	<2	<2	
Di-n-octyl phthalate	<2	<2	

Organic Compound

Polycyclic Aromatic Hydrocarbons	Blank µg/L	Test µg/L	Max Allowed
!External Lab Report No.	ES2035008	ES2035008	
Acenaphthene	<0.02	<0.02	
Acenaphthylene	<0.02	<0.02	
Anthracene	<0.02	<0.02	
Benzo(a)anthracene	<0.02	<0.02	
Benzo(a)pyrene	<0.005	<0.005	0.01 µg/L
Benzo(a)pyrene TEQ	<0.005	<0.005	
Benzo(b+j)fluoranthene	<0.02	<0.02	
Benzo(ghi)perylene	<0.02	<0.02	
Benzo(k)fluoranthene	<0.02	<0.02	
Chrysene	<0.02	<0.02	
Dibenzo(a-h)anthracene	<0.02	<0.02	
Fluoranthene	<0.02	<0.02	
Fluorene	<0.02	<0.02	
Indeno(123-cd)pyrene	<0.02	<0.02	
Naphthalene	<0.02	<0.02	
PAH - Total	<0.005	<0.005	
Phenanthrene	<0.02	<0.02	
Pyrene	<0.02	<0.02	



Corporate Accreditation No. 1115
Chemical and Biological Testing
Accredited for compliance with ISO/IEC 17025





Internet: www.awqc.com.au

Email: producttesting@awqc.com.au

FINAL REPORT

Report ID : 295678

Organic Compound

Organic Compound	Blank µg/L	Test µg/L	Max Allowed
Volatile Organic Compounds GCMS			
1 1 1 2-Tetrachloroethane	<1	<1	
1 1 1-Trichloroethane	<1	<1	
1 1 2 2-Tetrachloroethane	<1	<1	
1 1 2-Trichloroethane	<1	<1	
1 1-Dichloropropene	<1	<1	
1 2 3-Trichlorobenzene	<1	<1	
1 2 3-Trichloropropane	<1	<1	
1 2 4-Trichlorobenzene	<1	<1	
1 2 4-Trimethylbenzene	<1	<1	
1 2-Dibromo-3-chloropropane	<1	<1	1 µg/L
1 2-Dibromoethane	<1	<1	1 µg/L
1 2-Dichlorobenzene	<1	<1	1500 µg/L
1 2-Dichloroethane	<1	<1	3 µg/L
1 2-Dichloropropane	<1	<1	
1 3 5-Trimethylbenzene	<1	<1	
1 3-Dichlorobenzene	<1	<1	
1 3-Dichloropropane	<1	<1	
1 4-Dichlorobenzene	<1	<1	40 µg/L
1,1-Dichloroethane	<1	<1	
1,1-Dichloroethene	<1	<1	30 µg/L
2,2-Dichloropropane	<1	<1	
2-Chlorotoluene	<1	<1	
4-Chlorotoluene	<1	<1	
4-Isopropyltoluene	<1	<1	
Benzene	<1	<1	1 µg/L
Bromobenzene	<1	<1	
Bromochloromethane	<1	<1	
Bromodichloromethane	5	1	60 µg/L
Bromoform	2	1	100 µg/L
Bromomethane	<4	<4	
Carbon tetrachloride	<1	<1	3 µg/L
Chlorobenzene	<1	<1	300 µg/L
Chloroethane	<4	<4	
Chloroform	5	3	400 µg/L
Chloromethane	<4	<4	
cis-1 3-Dichloropropene	<1	<1	
cis-1,2-Dichloroethene	<1	<1	
Dibromochloromethane	6	3	150 µg/L
Dibromomethane	<1	<1	
Dichlorodifluoromethane	<1	<1	
Dichloromethane	<4	<4	4 µg/L
Ethylbenzene	<1	<1	300 µg/L
Hexachlorobutadiene	<0.7	<0.7	0.7 µg/L
Isopropylbenzene	<1	<1	
m+p-Xylenes - Total	<2	<2	



Corporate Accreditation No. 1115
Chemical and Biological Testing
Accredited for compliance with ISO/IEC 17025





Internet: www.awqc.com.au

Email: producttesting@awqc.com.au

FINAL REPORT

Report ID : 295678

Organic Compound

Organic Compound	Blank µg/L	Test µg/L	Max Allowed
Volatile Organic Compounds GCMS			
Naphthalene	<1	<1	
n-Butylbenzene	<1	<1	
n-Propylbenzene	<1	<1	
o-Xylene	<1	<1	
sec-Butylbenzene	<1	<1	
Styrene	<1	<1	30 µg/L
tert-Butylbenzene	<1	<1	
Tetrachloroethene	<1	<1	50 µg/L
Toluene	<1	<1	800 µg/L
Total 1,2-dichloroethene	<2	<2	60 µg/L
Total 1,3-dichloropropene	<2	<2	20 µg/L
Total Trichlorobenzene	<2	<2	30 µg/L
Total Xylene	<3	<3	600 µg/L
trans-1,3-Dichloropropene	<1	<1	
trans-1,2-Dichloroethene	<1	<1	
Trichloroethene	<1	<1	
Trichlorofluoromethane	<1	<1	
Trihalomethanes - Total	18	8	250 µg/L
Vinyl chloride	<0.3	<0.3	0.3 µg/L

Evaluation The product passed the requirements of clause 6.8 when tested at an exposure of 15000 mm² per Litre.

Number of Samples 1.

Test Comment Not applicable.

Qiong Huang

APPROVED SIGNATORY



Corporate Accreditation No. 1115
Chemical and Biological Testing
Accredited for compliance with ISO/IEC 17025

